

Technical Datasheet

AS810 PVC Slow Recovering Foam Tape

Product Description

- Colour: Black/White
- Density: 100-120Kgs/M³
- Width: 1000mm 1400mm
- Thickness: 2,3,4,5,6,8,10,12,15,18,20mm
- Roll Length: 25M to 130M according to the thickness.

Technical Data

Properties	Unit	Value	Test Method
Density	kgs/M³	100-125	
Tensile Strength	kpa	>150	DIN 53571
Elongation at Break	%	>120	DIN 53571
Tear Strength	N/mm	>80	DIN 53515
Compression Set	%	>45	DIN 53572
Compression Deflection	kpa	0s 12-33 60s 4-16	ASTM 1667
Shore 00 Hardness		20-40	-
Water Absorption	%	>30	-
Compression Water Seal	-	>30%	U-Test
Flammability	mm/min	<100/>6mm	FMVSS302
Temperature Range	°C	-30/+60	-

Data shown is conducted in a laboratory environment to stringent criteria, and is for a guideline only, we would always advise testing the substrates in the application prior to use. Chemical Resistance can vary greatly due to a number of exposure parameters including: Temperature, Concentration, Duration of exposure, and bond line thickness. The information in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products. For which reason the information in this publication is given without responsibility



Technical Datasheet

S-4210 MF Adhesive Double Sided Tape

Product Description

The MF-adhesive is a modified polyacrylate and has good, all-round adhesive properties especially with reference to ageing and weathering properties. It has very good initial tack with very high peel adhesion to a wide variety of low surface energy substrates such as foams, PE, PP and EPDM. MF-adhesive is an ideal lamination adhesive for a wide variety of laminates.

Product Structure		
	Support	Non-woven, 12 g/m²
	Interliner	Release paper, yellow, 90 g/ m²
	Adhesive weight	90 g/m²
	Total Thickness	0,10mm
Characteristics		
	Temperature resistance (according to the ATP test method AA-B-12-07)	-40°C to +90 °C
	Adhesive strength (according to AFERA 5001)	min 21 N/25mm Contact time: 1h

Data shown is conducted in a laboratory environment to stringent criteria, and is for a guideline only, we would always advise testing the substrates in the application prior to use. Chemical Resistance can vary greatly due to a number of exposure parameters including: Temperature, Concentration, Duration of exposure, and bond line thickness. The information in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products. For which reason the information in this publication is given without responsibility