



## Technical Datasheet

# MBS J6XL D3 PVA Adhesive

### Technical Data

|                    |                      |                             |
|--------------------|----------------------|-----------------------------|
| Solids Contents:   | 48-51%               | Infra Red Moisture Analyser |
| Viscosity:         | 7,000-12,000cPs      | Brookfield RVF 5/20/23°C    |
| Using Temperature: | Ambient              |                             |
| Dilution:          | Use neat as received |                             |

### Application Information

|                         |   |
|-------------------------|---|
| Main Usage:             | High quality wood adhesive. All joinery where D3 water resistance is required e.g. worktops, cubicles, kitchen & bathroom panels. |
| Machine Types:          | All roller Systems  |
| Running Speeds:         | Dependent on machine type and compression time HPL, plywood, chipboard, MDF, soft & hardwood.                                     |
| Additional Information: | High water resistance D3 EN204  |
| Storage:                | Store between 5 - 25°C, Storage outside of the suggested temperature range could adversely affect the properties of the adhesive. |