

Scapa AS1230

Acrylic Foam Tape (AFT) - 0.64mm, Grey, High Temperature, Pre-Powder Coat

DESCRIPTION

AS1230 is a conformable double sided acrylic foam tape with a release liner on one side. The product is used for permanent bonding of materials such as metals, glass and some plastics, in interior and exterior applications.

APPLICATIONS

- Bonding metal to metal before passing through the powder coat painting process.
- Panel fixation, metal stiffener and reinforcement bar bonding: doors, lifts, trailers, cabinets, traffic signs, etc.
- Bonding and sealing in the photovoltaic (PV) solar module industry – framing of crystalline silicon panels.

PRODUCT BENEFITS

- Withstands expansion and contraction of materials without loss of adhesion due to its visco-elastic properties.
- Very high adhesion to metals and glass.
- Very high resistance to static and dynamic loads.
- Suitable for indoor and outdoor use (excellent UV and ageing resistance).
- Solvent free product
- Complies with Directive 2002/95/EC (RoHS) restricting the use of heavy metals in electronics products.
- Service temperature: -30°C to +150°C continuous, and to +210°C peak (duration 1 hour).

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
90° Peel Adhesion 20 min Glass	30	N/25mm	ASTM D330: PSTC 101
90° Peel Adhesion 20 min Steel	40	N/25mm	ASTM D330: PSTC 101
90° Peel Adhesion 24 hr Glass	40	N/25mm	ASTM D330: PSTC 101
90° Peel Adhesion 24 hr Steel	52.5	N/25mm	ASTM D3330
Density	640	Kg/m ³	Mass-Volume
Dynamic Shear Steel	480	N/(25mm)	ASTM D1002 24hr dwell
Elongation	800	%	ASTMD882
Rolling Ball Tack #14 (5.604g)	>300	mm	ASTM D3121 PSTC 6M
Rolling Ball Tack #24 (28.2g)	>300	mm	ASTM D3121 PSTC 6M
Static Shear 15KPa @ 93°C	>10,000	Min	ASTM D3654 PSTC 107M
Static Shear 23KPa @ 93°C	>10,000	Min	ASTM D3654
Static Shear Steel 25°C	1,440	Min	ASTM D3654
Tensile Strength	10	N/25mm	ASTMD882

Note:

Static shear stainless steel 25°C, 0.5 square inch, 24 hour dwell time, 2.5 kg for 24 hours.

STANDARD PRESENTATIONS

- Colours: Grey
- Core: 76mm, Plain plastic
- Packaging: Cardboard, bulk packed with silicone interleaving between layers
- Roll Length: 33 metres
- Roll Width: On request from 6mm to max. 900 mm.
- Release Liner : red, polyethylene (PE)

RECOMMENDATIONS

Rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. The ideal storage temperature should be between 10°C and 30°C with relative humidity at 30 to 70%. The shelf life is 24 months from the date of manufacture. Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.